



Queens Road Penkhull
Stoke-on-Trent ST4 7LQ
Tel: +44 (0) 1782 764444
Fax: +44 (0) 1782 412331
E-mail: info@ceram.com
http://www.ceram.com

PHYSICAL TESTING REPORT

TopCer Industria de Ceramica Lda
Z Industria de Oia
3770-908 Oia
Portugal

FAO: Dr M Rodrigues/J Dt

REPORT OF TESTS ON: Unglazed Porcelain Tiles

Your Reference: 6601RT 146x146mm

CERAM Reference: (086579)-29996

Date Reported 08-Oct-2008

Order Number: Paid by Bacs

Date Logged 02-Oct-2008

Date(s) of Test(s): 02-Oct-2008 to 07-Oct-2008

Inclined Platform Test for Slip Resistance of Flooring Materials Under Wet Barefoot Conditions

DIN 51097: 1992

No.	Operator 1- Angle of Inclination	Operator 2- Angle of Inclination
1	30.0	30.0
2	30.0	30.0
3	30.0	30.0
4	30.0	30.0

Description of Test Specimen(s): 1m X 0.5m panel

Average Barefoot Result: 30.0 °

Category: C

The critical angle at which 2 test persons reach the limit of safe walking on an inclined plane is used as a measure of slip resistance.

End of Test Report


S Hall
Authorised Signatory

