



Queens Road Penkhull  
Stoke-on-Trent ST4 7LQ  
Tel: +44 (0) 1782 764444  
Fax: +44 (0) 1782 412331  
E-mail: info@ceram.com  
http://www.ceram.com

## PHYSICAL TESTING REPORT

**TopCer Industria de Ceramica Lda**  
Z Industria de Oia  
3770-908 Oia  
Portugal

FAO: Dr M Rodrigues/J Dt

**REPORT OF TESTS ON:** Unglazed Porcelain Tiles

**Your Reference:** 6601SS 146x146mm

**CERAM Reference:** (086579)-29998

**Date Reported** 08-Oct-2008

**Order Number:** Paid by Bacs

**Date Logged** 02-Oct-2008

**Date(s) of Test(s):** 02-Oct-2008 to 07-Oct-2008

Inclined Platform Test for Slip Resistance of Flooring Materials Under Wet Barefoot Conditions

DIN 51097: 1992

No.	Operator 1- Angle of Inclination	Operator 2- Angle of Inclination
1	30.0	30.0
2	30.0	30.0
3	30.0	30.0
4	30.0	30.0

Description of Test Specimen(s): 1m X 0.5m panel  
Average Barefoot Result: 30.0 °  
Category: C

The critical angle at which 2 test persons reach the limit of safe walking on an inclined plane is used as a measure of slip resistance.

**End of Test Report**

  
S Hall  
Authorised Signatory

